



SHEET METAL CONNECTORS, INC.

MINNEAPOLIS, MN
5850 Main Street N.E.
Minneapolis, Minnesota 55432
LOCALLY CALL: 763-572-0000
TOLL FREE: 1-800-328-1966
FAX: 763-572-1100

www.smduct.com

ROCKFORD, IL
5601 Sandy Hollow Road
Rockford, Illinois 61109
LOCALLY CALL: 815-874-4600
TOLL FREE: 1-866-504-4600
FAX: 815-874-9979



Submittal Sheet

BUTYL TAPE

Butyl Tape	3/16" x 5/8"	(30' rolls - 750' per box)
-------------------	---------------------	-----------------------------------

DESCRIPTION - Sealers Rubber Seal is a one component non-drying permanently flexible material designed for sealing rigid and expansion joints between all combination of wood, glass, metal and masonry surfaces without a primer.

Composition -	Butyl rubber, resins, inert pigments
Odor -	Nil - will not contaminate sweet butter
Color -	Gray - ASTM-D1729-69
Weight Per Gallon -	12 to 13 pounds - ASTM-D71-72
Percent Solids -	Theoretical 90% - ASTM-C771-74
Percent Shrinkage -	15% Maximum
Low Temperature Flexibility -	No cracking, separation or loss of adhesion of a ___" diameter bead on galvanized steel when bent at - 60°F over a 1/2" mandrel. ASTM-C-711-72 ASTM-C763-73
Adhesion -	Adheres to oily metal surfaces, painted and unpainted galvanized steel or aluminum. Test per AAMA 809.2 1976, paragraph 4.1.
Moisture Vapor Transmission (MVT) -	Less than 1.0 gram per day per M2, 20 mil, ASTM-E-96.
Slump -	Maximum slump of 3/16" at 210°F ASTM-D-2202.
Bubble Formation -	Will not exceed 25% of surface after 72 hours at 160°F.